applying the metallic anti-oxidation coating to the gas turbine blade; and subjecting the coated gas turbine blade to a postheat treatment, wherein the postheat treatment follows the application of the coating in such a way that the temperature of the gas turbine blade, after the application of the coating and before the postheat treatment, is at least equal to a minimum temperature, the minimum temperature being relatively higher than room temperature.

- 2. (Amended) The method as claimed in claim 1, wherein the minimum temperature is about 500 K.
- 3. (Amended) The method as claimed in claim 1, wherein the application of the metallic coating to the gas turbine blade is effected in a coating region of the vacuum plant and the postheat treatment is effected in a postheat treatment region of the vacuum plant, the coating region and the postheat treatment region being different regions of the vacuum plant.
- 4. (Amended) The method as claimed in claim 3, wherein the coated gas turbine blade is automatically transferred from the coating region into the postheat treatment region.
- 5. (Amended) The method as claimed in claim 1, further comprising:

 cooling down the gastturbine blade subjected to postheat treatment, to room temperature in a controlled manner.
- 6. (Amended) The method as claimed in claim 3, wherein a first number of gas turbine blades is located in the coating region and nearly simultaneously, a second number of gas turbine blades is located in the postheat treatment region, the second number being larger than the first number.

7. (Amended) The method as claimed in claim 1, wherein a material used for the gas turbine blade is one of a nickel-, iron-, or cobalt-base superalloy.

- 8. (Amended) The method as claimed in claim 1, wherein the metallic anti-oxidation coating is an MCrAlX alloy, where M stands for one or more elements of the group including iron, cobalt and nickel; Cr stands for chromium; Al stands for aluminum; and X stands for one or more elements of the group including yttrium, rhenium and the elements of the rare earths.
- 9. (Amended) An apparatus for coating a gas turbine blade with a metallic antioxidation coating in a vacuum plant, comprising:
 - a coating chamber; and
- a postheat treatment chamber, wherein the postheat treatment chamber is connected to the coating chamber in a vacuum-tight manner.
- 10. (Amended) The apparatus as claimed in claim 9, wherein a heating device is provided in the postheat treatment chamber.
- 11. (Amended) The apparatus as claimed in claim 9, further comprising:

 a preheating chamber, the preheating chamber being arranged upstream of the coating chamber and being connected to the coating chamber in a vacuum-tight manner.
 - 12. (Amended) The apparatus as claimed in claim 9, further comprising:
- a cooling chamber, the cooling chamber being arranged downstream of the postheat treatment chamber and being connected to the postheat treatment chamber in a vacuum-tight manner.

New U.S. Application Docket No.: 3286-0169P

13. (Amended) The apparatus as claimed in claim 9, wherein the vacuum-tight connection between the coating chamber and the postheat treatment chamber is produced via a lock chamber.

- 14. (Amended) The apparatus as claimed in claim 13, wherein a heating device is provided in the lock chamber.
- 15. (Amended) The apparatus as claimed in claim 9, further comprising:

 a transfer system for the automatic transfer of the gas turbine blade from one chamber into another chamber of the vacuum plant.
- 16. (Amended) The apparatus as claimed in claim 9, wherein the coating chamber includes a first receiving capacity and the postheat treatment chamber includes a second receiving capacity for gas turbine blades, the second receiving capacity being greater than the first receiving capacity.

Please add the following new claims:

- -- 17. The method of claim 1, wherein the minimum temperature ranges from about 900K to about 1400 K.
- 18. The method as claimed in claim 2, wherein the application of the metallic coating to the gas turbine blade is effected in a coating region of the vacuum plant and the postheat treatment is effected in a postheat treatment region of the vacuum plant, the coating region and the postheat treatment region being different regions of the vacuum plant.

ij

19. The apparatus as claimed in claim 11, further comprising:

a cooling chamber, the cooling chamber being arranged downstream of the postheat treatment chamber and being connected to the postheat treatment chamber in a vacuum-tight manner.

- 20. The apparatus as claimed in claim 11, wherein the vacuum-tight connection between the coating chamber and the postheat treatment chamber is produced via a lock chamber.
- 21. The apparatus as claimed in claim 12, wherein the vacuum-tight connection between the coating chamber and the postheat treatment chamber is produced via a lock chamber.
- 22. The apparatus as claimed in claim 11, wherein a heating device is provided in the lock chamber.
- 23. The apparatus as claimed in claim 12, wherein a heating device is provided in the lock chamber.
- 24. The apparatus as claimed in claim 19, wherein a heating device is provided in the lock chamber.
- 25. The apparatus as claimed in claim 20, wherein a heating device is provided in the lock chamber.
- 26. The apparatus as claimed in claim 21, wherein a heating device is provided in the lock chamber.
- 27. The method as claimed in claim 5, wherein the metallic anti-oxidation coating is an MCrAlX alloy, where M stands for one or more elements of the group including iron,

Docket No.: 3280-0109P

cobalt and nickel; Cr stands for chromium; Al stands for aluminum; and X stands for one or more elements of the group including yttrium, rhenium and the elements of the rare earths.

- 28. The method as claimed in claim 7, wherein the metallic anti-oxidation coating is an MCrAlX alloy, where M stands for one or more elements of the group including iron, cobalt and nickel; Cr stands for chromium; Al stands for aluminum; and X stands for one or more elements of the group including yttrium, rhenium and the elements of the rare earths.
- 29. The apparatus as claimed in claim 11, wherein the vacuum-tight connection between the coating chamber and the preheating chamber is produced via a lock chamber.
- 30. The apparatus as claimed in claim 12, wherein the vacuum-tight connection between the cooling chamber and the postheat treatment chamber is produced via a lock chamber.
- 31. The apparatus as claimed in claim 29, wherein a heating device is provided in the lock chamber.
- 32. The apparatus as claimed in claim 30, wherein a heating device is provided in the lock chamber.
 - 33. A vacuum plant, comprising:

a coating chamber, wherein a gas turbine blade is coated with a metallic antioxidation coating; and

a postheat treatment chamber, wherein the coated gas turbine blade is subjected to heat treatment,

wherein a temperature of the gas turbine blade, after coating and before postheat treatment, is at least equal to a minimum temperature which is relatively higher than

at room temperature.

The vacuum plant of claim 33, wherein the minimum temperature is about 500 K.

- 35. The vacuum plant of claim 33, wherein the minimum temperature ranges from about 900K to about 1400 K.
- 36. The vacuum plant of claim 33,, wherein the coating chamber and the postheat treatment chamber are connected in a vacuum tight manner.
 - 37. The vacuum plant of claim 36, further comprising:

a preheating chamber, the preheating chamber being arranged upstream of the coating chamber and being connected to the coating chamber in a vacuum-tight manner.

38. The vacuum plant of claim 36, further comprising:

a cooling chamber, the cooling chamber being arranged downstream of the postheat treatment chamber and being connected to the postheat treatment chamber in a vacuum-tight manner.

39. The vacuum plant of claim 37, further comprising:

a cooling chamber, the cooling chamber being arranged downstream of the postheat treatment chamber and being connected to the postheat treatment chamber in a vacuum-tight manner.

- 40. The vacuum plant of claim 36, wherein the vacuum-tight connection between the coating chamber and the postheat treatment chamber is produced via a lock chamber.
 - 41. The vacuum plant of claim 36, further comprising:

 a transfer system for the automatic transfer of the gas turbine blade from one